

Sizes of Open-Graded Course Aggregates

% Passing Sieve Openings

| Va. Size No. | 4 in. | 3 1/2 in. | 3 in. | 2 1/2 in. | 2 in. | 1 1/2 in. | 1 in. | 3/4 in. | 1/2 in. | 3/8 in. | No. 4 | No. 8 | No. 16 | No. 50 | No. 100 |
|--------------|---------|-----------|----------|-----------|--------|-----------|--------|----------|---------|---------|---------|---------|--------|--------|---------|
| 1 | Min 100 | 90-100 | | 25-60 | | Max. 15 | | Max. 5 | | | | | | | |
| 2 | | | Min. 100 | 95-100 | 35-70 | Max. 15 | | Max. 5 | | | | | | | |
| 3 | | | | Min. 100 | 90-100 | 35-70 | 0-15 | | Max. 5 | | | | | | |
| 357 | | | | Min. 100 | 90-100 | | 35-70 | | 10-30 | | Max. 5 | | | | |
| 57 | | | | | | Min. 100 | 95-100 | | 25-60 | | Max. 10 | Max. 8 | | | |
| 78 | | | | | | | | Min. 100 | 90-100 | 40-75 | 5-25 | Max. 10 | Max. 5 | | |

* From VDOT Road and Bridge Specifications, 2007

Due to variations in sizing from one quarry to another, refer to chart above for proper stone sizing when ordering stone.

| | | |
|-----------------------|--|------|
| Stone Sizing Schedule | | Date |
| Designed | | |
| Drawn | | |
| Checked | | |
| Approved | | |

